

## **PRODUCT BULLETIN**

*Materials Research Group LD89 glass:*

Ready to press glass used to manufacture preforms for compression seals.

*Technical data:*                      Coefficient of Expansion from 25°C to 300°C:  $89 \times 10^{-7}$   
   Annealing Temperature: 445°C  
   Softening Point: 648°C  
   Firing Temperature: 950°C  
   Melt Density: 2.26 g/cc minimum

\*The information contained in this product bulletin is believed to be reliable. Since the conditions of application and use of our products are beyond our control, no warranty or representation is expressed or implied regarding the accuracy of the information.

Date Issued: 6-23-17

---