

PRODUCT BULLETIN

Materials Research Group LT84 glass:

Ready to press low temperature lead glass.

Technical data:

Coefficient of Expansion from 25°C to 260°C: 84×10^{-7}
Transition Temperature: 295°C
Annealing Temperature: 315°C
Softening Point: 350°C
Firing Temperature: 380°C
Density: 5.8 g/cc reference

*The information contained in this product bulletin is believed to be reliable. Since the conditions of application and use of our products are beyond our control, no warranty or representation is expressed or implied regarding the accuracy of the information.

Date Issued: 2/11/11