

## PRODUCT BULLETIN

*Materials Research Group SL90 glass:*

Ready to press soda lime glass used to manufacture preforms for compression seals.

*Technical data:*                      Coefficient of Expansion 25°C to 300°C:  $93 \times 10^{-7}$   
Softening Point: 700°C

\*The information contained in this product bulletin is believed to be reliable. Since the conditions of application and use of our products are beyond our control, no warranty or representation is expressed or implied regarding the accuracy of the information.

Date Issued: 11/10/09